

# BUA FAH

## MIXED CEMENT



**Bua Fah** brand is a Mixed cement manufactured in compliance with Thai Industrial Standard 80-2550.

This brand of cement is suitable for;

- Brick laying works
- Plastering works
- Small-scale construction works



### Mix proportioning for application



### Specifications for Mixed Cement

Specifications		TIS 80-2550	Typical Bua Fah Brand
<b>Standard Physical requirements</b>			
Blaine fineness, cm <sup>2</sup> /gm	Min.	3200	5000
Autoclave expansion, %	Max. %	0.8	0.2
<b>Vicat setting time</b>			
Initial set	Min. Minute	45	70
Air content of mortar	Max. %	12	10
<b>Compressive strength, MPa</b>			
3 Days	Min.	6.9	10.0
7 Days	Min.	11.8	14.0
False set, final penetration	Min. %	50	80

