

BUA SUPER

MIXED CEMENT



Bua Super brand is a Mixed cement manufactured in compliance with Thai Industrial Standard 80-2550, 40 Kg.

This brand of cement is suitable for;

- Brick laying works
- Plastering works
- Small-scale construction works



Mix proportioning for application



Specifications for Mixed Cement

Specifications		TIS 80-2550	Typical Bua Super Brand
Standard Physical requirements			
Blaine fineness, cm ² /gm	Min.	3200	5200
Autoclave expansion, %	Max. %	0.8	0.2
Vicat setting time			
Initial set	Min. Minute	45	70
Air content of mortar	Max. %	12	10
Compressive strength, MPa			
3 Days	Min.	6.9	14.0
7 Days	Min.	11.8	18.0
False set, final penetration	Min. %	50	80

